



Name of article	Allure 1000	Secondary backing ISO 2424	Action back
Method of production ISO 2424	Tufted	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Loop	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Style	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100% Econyl by Aquafil	Water fastness EN ISO 105 E01	≥ 4
Primary backing ISO 2424	PES	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 2300 g/m ²	Stitch rate ISO 1763	ca. 130.700/m ²
Overall thickness ISO 1765	ca. 7,0 mm		
Pile service weight	ca. 1000 g/m ²		



EN 14041 | DOP: 1060-OC-3379
CPR: 1658-CPR-3379 | NB: 1658

Health-promoting properties AIR



- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers

HEALTH



70 710 3720-1



Health-promoting ACOUSTIC properties



- Improved impact sound insulation +26dB
- Enhanced room acoustics +0.2α_w

Hz	125	250	500	1000	2000	4000
α _s	0,00	0,05	0,10	0,35	0,45	0,50

- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective



Environmental properties

33FBBFC4
PRODID | product pass

- 100% recycled yarn
- Recycled primary backing
- Easy cleaning with water only



Product Information

The staggered tufting process gives the loop quality a distinctive look. At the same time, the surface design gives the product typical properties in terms of delayed regeneration behavior. Indentations in the fibers recover after a short period of use.

Installation Instructions

The seam is cut professionally from above inside the nap alley using a seam cutter, such as the one from Mittag. During this work process, it must be ensured that the nap alley is not left during cutting.



Made in Europe (production according to EU standard)