Characteristic features EN 1307

Name of article Method of production ISO 2424 Width ISO 3018 Surface structure ISO 2424 Colourways Pile material ISO 2424 Primary backing ISO 2424 Overall weight ISO 8543 Overall thickness ISO 1765 Pile service weight	Craze x Chase Tufted ca. 400 Loop Mix 100% Econyl by Aquafil PES ca. 2190 g/m ² ca. 5 mm ca. 660 g/m ²	Secondary backing ISO 2424 Electrostatic loading ISO 6356 Surface resistivity ISO 10965 ROT Transparency to heat ISO 8302 Light fastness ISO 105-B02 Water fastness EN ISO 105 E01 Friction fastness EN ISO 105-X12 Stitch rate ISO 1763	Action back <2 KV 10 ⁹ Ω 0,09 K*m ² /W ≥ 5 ≥ 4 ≥ 3-4 ca. 215000/m ²
		CE EN 14041 DOP: 1060-OC-0139-02 CPR: 25-000139-02 NB: 1658	
 Health-promoting properties AIR O Free from PVC and bitumen. Free from formaldehyde. Reduction of fine dust in the breathing air. 		Health-promoting ACOUSTIC properties 𝔅 • Improved impact sound insulation +20dB Enhanced room acoustics +0.2aw . • Hz 125 250 500 1000 2000 4000	

HEALTH

- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors. •

Environmental properties

- TVOC limits are immediately met.
- Suitable for allergy sufferers

AOEFB7FE PRODIS-ID | product po

- 100% recycled yarn
- Recycled primary backing
- Easy cleaning with water only



Product Information

 α_{s}

0,01

Acoustically effective

0,05

through enhanced well-being

0,08

Increased employee concentration and motivation

0,25

0,18

0,20

The randomly appearing melange pattern of the tufting creates a lively appearance. The delayed regeneration behavior of the loop quality is typical of the fabric. Indentations in the fibers recover after a short period of frequent use.

Installation Instructions

The seam is cut professionally from above within the nap alley using a seam cutter (e.g. from Mittag). During this work process, it must be ensured that the nap alley is not left during cutting.

Data status 30.06.2025. Subject to changes due to technical advancements.

