



Name of article	<b>Dune 700</b>	Secondary backing ISO 2424	Action back
Method of production ISO 2424	Tufted	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 <sup>9</sup> Ω
Surface structure ISO 2424	Loop	Transparency to heat ISO 8302	0,09 K*m <sup>2</sup> /W
Colourways	Style	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100% Econyl by Aquafil	Water fastness EN ISO 105 E01	≥ 4
Primary backing ISO 2424	PES	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 1510 g/m <sup>2</sup>	Stitch rate ISO 1763	ca. 248.900/m <sup>2</sup>
Overall thickness ISO 1765	ca. 6.0 mm		
Pile service weight	ca. 710 g/m <sup>2</sup>		



EN 14041 | DOP: | NB: 1658

## Health-promoting properties AIR



- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers

HEALTH



## Health-promoting ACOUSTIC properties



- Improved impact sound insulation +25dB
- Enhanced room acoustics +0.2α<sub>w</sub>

Hz	125	250	500	1000	2000	4000
α <sub>s</sub>	0,01	0,05	0,10	0,25	0,44	0,45

- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective

## Environmental properties

OEA27A03

PRODID | product pass

- Recycled primary backing
- Easy cleaning with water only



## Product Information

DUNE impresses with its fascinating two-tone loop structure and individual design. The patternless installation creates a particularly characteristic surface appearance.

## Installation Instructions

The precise seam cut is carried out professionally using a steel ruler and a laying knife with a trapezoidal blade. The use of pile scissors is recommended for processing cut studs to ensure a flawless appearance.



Made in Europe (production according to EU standard)