Characteristic features EN 1307



Name of article

Method of production ISO

2424

Width ISO 3018

Surface structure ISO 2424

Colourways

Pile material ISO 2424

Primary backing ISO 2424

Overall weight ISO 8543 Overall thickness ISO 1765

Pile service weight

ECO Solo

Getuftet

ca. 400 Schlinge

Uni

100 % Polyamid Econyl by

Aquafil

PES

ca. 2000 g/m^2

ca. 5.9 mm

ca. 700 g/m^2

Secondary backing ISO 2424

Electrostatic loading ISO 6356 Surface resistivity ISO 10965 ROT

Transparency to heat ISO 8302

Light fastness ISO 105-B02 Water fastness EN ISO 105 E01

Friction fastness EN ISO 105-X12

Stitch rate ISO 1763

Action back < 2 KV

 $10^9 \Omega$

 $0.09 \, K^* m^2 / W$

> 5

4 > 3-4

ca. $184000/m^2$



















EN 14041 | DOP: 1060-OC-3379 CPR: 1658-CPR-3379 | NB: 1658











Health-promoting properties AIR



- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers



70 710 3720-1







Health-promoting ACOUSTIC properties



- Improved impact sound insulation +27dB Enhanced room acoustics $+0.2\alpha_{\omega}$
 - 125 250 500 1000 2000 4000 0, 0, 0,
- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective

Environmental properties

B6BF14B0



- Recycled primary backing
- Easy cleaning with water only

Product Information

ECO SOLO impresses with its fascinating two-tone loop structure and individual design. The patternless installation creates a particularly characteristic surface appearance.

Installation Instructions

The precise seam cut is carried out professionally using a steel ruler and a laying knife with a trapezoidal blade. The use of pile scissors is recommended for processing cut studs to ensure a flawless appearance.

















Made in Europe (production according to EU standard)

Data status 30.06.2025. Subject to changes due to technical advancements.