



Name of article	Eddy	Secondary backing ISO 2424	Action back
Method of production ISO 2424	Tufted	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Cut	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Uni	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100% PET	Water fastness EN ISO 105 E01	≥ 4
Primary backing ISO 2424	PP	Friction fastness EN ISO 105-X12	≥ 4
Overall weight ISO 8543	ca. 2950 g/m ²	Stitch rate ISO 1763	ca. 97.350/m ²
Overall thickness ISO 1765	ca. 13,0 mm		
Pile service weight	ca. 2050 g/m ²		



EN 14041 | DOP: 1060-OC-3565
CPR: 1658-CPR-3565 | NB: 1658

Health-promoting properties AIR



- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers

HEALTH



Health-promoting ACOUSTIC properties



- Improved impact sound insulation +28dB
- Enhanced room acoustics +0.3α_w
- | Hz | 125 | 250 | 500 | 1000 | 2000 | 4000 |
|----------------|-----|-----|-----|------|------|------|
| α _s | 0, | 0, | 0, | 0, | 0, | 0, |
- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective

Environmental properties

PRODIS-ID | product pass

- Recycled primary backing
- Easy cleaning with water only



Product Information

The voluminous cut pile is characterized by deliberately incorporated iridescent shadows, which reveal a varying fibre level. This unique property gives the carpet a special characteristic and plays a key role in its design.

Installation Instructions

In order to ensure a precise seam cut within the nap alley, the nap alley must first be opened with a pile reamer before making an accurate cut with a seam cutter (e.g. from Mittag).



Made in Europe (production according to EU standard)