



Name of article	Factum	Secondary backing ISO 2424	Action back
Method of production ISO 2424	Getuftet	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Velours	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Mix	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100 % Polyamid Econyl by Aquafil	Water fastness EN ISO 105 E01	4
Primary backing ISO 2424	PES	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 1620 g/m ²	Stitch rate ISO 1763	ca. 192500/m ²
Overall thickness ISO 1765	ca. 7,0 mm		
Pile service weight	ca. 900 g/m ²		




EN 14041 | DOP: 1060-OC-3547
CPR: 1658-CPR-3547 | NB: 1658

Health-promoting properties AIR



- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers

HEALTH



Health-promoting ACOUSTIC properties



- Improved impact sound insulation +25dB
- Enhanced room acoustics +0.2α_w
- | Hz | 125 | 250 | 500 | 1000 | 2000 | 4000 |
|----------------|------|------|------|------|------|------|
| α _s | 0,00 | 0,05 | 0,10 | 0,25 | 0,50 | 0,57 |
- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective



Environmental properties

BD2DD9DE
PRODUS-ID | product pass

- 100% recycled yarn
- Recycled primary backing
- Easy cleaning with water only



Product Information

The crimped velour with a discreetly grainy structure is characterized by deliberately incorporated iridescent shadows that reveal a varying fibre level. This unique property gives the carpet a special characteristic and plays a key role in the design.

Installation Instructions

In order to ensure a precise seam cut within the nap alley, the nap alley must first be opened with a pile reamer before making an accurate cut with a seam cutter (e.g. from Mittag).



Made in Europe (production according to EU standard)