

Characteristic features EN 1307



Name of article	AT Fishbone 600	Secondary backing ISO 2424	Welltex® Acoustic
Method of production ISO 2424	Tufted	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 50x50	Surface resistivity ISO 10965 ROT	10 <sup>9</sup> Ω
Surface structure ISO 2424	Loop	Transparency to heat ISO 8302	0,09 K*m² /W
Colourways	Style	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100% Econyl by Aquafil	Water fastness EN ISO 105 E01	≥ 4
Primary backing ISO 2424	PES	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 2000 g/m²	Stitch rate ISO 1763	ca. 315.000/m²
Overall thickness ISO 1765	ca. 5,5 mm		
Pile service weight	ca. 540 g/m²		



EN 14041 | DOP: 1060 OC 3497 | NB: 1658

Health-promoting properties AIR

- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers

HEALTH

Health-promoting ACOUSTIC properties

- High acoustic effectiveness as standard
- Improved impact sound insulation +26dB  
Enhanced room acoustics +0.2α<sub>w</sub>
- | Hz             | 125  | 250  | 500  | 1000 | 2000 | 4000 |
|----------------|------|------|------|------|------|------|
| α <sub>s</sub> | 0,00 | 0,04 | 0,17 | 0,22 | 0,28 | 0,32 |
- Increased employee concentration and motivation through enhanced well-being

Environmental properties

38844088  
PRODID-ID | product pass

- Completely recyclable
- 100% recycled yarn
- Recycled primary backing
- 100% recycled secondary backing
- Weight reduction of up to 50%
- Easy cleaning with water only

Product Information

Installation Instructions



Made in Europe (production according to EU standard)