



Name of article	Forest 700	Secondary backing ISO 2424	Action back
Method of production ISO 2424	Getuftet	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Velours	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Style	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100 % Polyamid Antron®	Water fastness EN ISO 105 E01	≥ 4
Primary backing ISO 2424	PES	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 1390 g/m ²	Stitch rate ISO 1763	ca. 189500/m ²
Overall thickness ISO 1765	ca. 6,4 mm		
Pile service weight	ca. 690 g/m ²		



EN 14041 | DOP: | NB: 1658

Health-promoting properties AIR



- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers

HEALTH



Health-promoting ACOUSTIC properties



- Improved impact sound insulation +31dB
- Enhanced room acoustics +0.2α_w

Hz	125	250	500	1000	2000	4000
α _s	0,01	0,05	0,10	0,25	0,50	0,57

- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective

Environmental properties

EC3360CD
PRODISE ID | product pass

- 100% recycled yarn
- Recycled primary backing
- Easy cleaning with water only



Product Information

FOREST impresses with its fascinating two-tone loop structure and individual design. The patternless installation creates a particularly characteristic surface appearance.

Installation Instructions

The precise seam cut is carried out professionally using a steel ruler and a laying knife with a trapezoidal blade. The use of pile scissors is recommended for processing cut studs to ensure a flawless appearance.



Made in Europe (production according to EU standard)

Data status 23.07.2024. Subject to changes due to technical advancements.