Characteristic features EN 1307



Name of article

Method of production ISO 2424

Width ISO 3018

Surface structure ISO 2424

Colourways

Pile material ISO 2424

Primary backing ISO 2424

Overall weight ISO 8543

Overall thickness ISO 1765

Pile service weight

FORUM Velours

Tufted

ca. 400

Cut

Style

100% PA 6

PES

ca. 2200 g/m²

ca. 9.7 mm

ca. 1000 g/m^2

Welltex Circular® Acoustic Secondary backing ISO 2424

Electrostatic loading ISO 6356 < 2 KV

Surface resistivity ISO 10965 ROT $10^9 \Omega$

 $0.09 \, K^* m^2 / W$ Transparency to heat ISO 8302

Light fastness ISO 105-B02 > 5 Water fastness EN ISO 105 E01 > 4 Friction fastness EN ISO 105-X12

Stitch rate ISO 1763 ca. 197.500/m²































EN 14041 | DOP: 1060-OC-3548 CPR: 1658-CPR-3548 | NB: 1658

Health-promoting properties AIR



- Free from PVC and bitumen.
- Free from latex and fillers.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers









Health-promoting ACOUSTIC properties



- High acoustic effectiveness as standard
- Improved impact sound insulation +30dB Enhanced room acoustics $+0.3\alpha$
- 1000 Hz 125 250 500 2000 4000 0,05 0,51 0,30 0,40 0,50

> 3-4

Increased employee concentration and motivation through enhanced well-being

Environmental properties

9295BC10



- Recycled primary backing
- 100% recycled secondary backing
- · Easy cleaning with water only

Product Information

The cut pile is characterized by deliberately incorporated iridescent shadow formations that reveal a varying fibre level. This unique property gives the carpet a special characteristic and plays a key role in its design.

Installation Instructions

In order to ensure a precise seam cut within the nap alley, the nap alley must first be opened with a pile reamer before making an accurate cut with a seam cutter (e.g. from Mittag).





















Made in Europe (production according to EU standard)

Data status 30.06.2025. Subject to changes due to technical advancements.