## **Characteristic features EN 1307**

Name of article	AT FORUM Velours	Secondary backing ISO 2424	Welltex Circular® Acoustic
Method of production ISO 2424	Tufted	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 50x50	Surface resistivity ISO 10965 ROT	10º Ω
Surface structure ISO 2424	Cut	Transparency to heat ISO 8302	0,09 K*m² /W
Colourways	Style	Light fastness ISO 105-B02	$\geq 5$
Pile material ISO 2424	100% PA 6	Water fastness EN ISO 105 E01	$\geq$ 4
Primary backing ISO 2424	PES	Friction fastness EN ISO 105-X12	$\geq$ 3-4
Overall weight ISO 8543	ca. 2200 g/m²	Stitch rate ISO 1763	ca. 197.500/m²
Overall thickness ISO 1765	ca. 9,7 mm		
Pile service weight	ca. 1000 g/m²		
Pile material ISO 2424 Primary backing ISO 2424 Overall weight ISO 8543 Overall thickness ISO 1765	100% PA 6 PES ca. 2200 g/m <sup>2</sup> ca. 9,7 mm	Water fastness EN ISO 105 E01 Friction fastness EN ISO 105-X12	$\geq 4$ $\geq 3-4$



PRODIS-ID | product pass

• Completely recyclable

- Recycled primary backing
- 100% recycled secondary backing

**Environmental properties** 

- Weight reduction of up to 50%
- Energy-efficient coating technology without the use of gas and water
- The only carpet worldwide that can be 100% recycled into its components (True circular economy)
- Easy cleaning with water only



## **Product Information**

The cut pile is characterized by deliberately incorporated iridescent shadow formations that reveal a varying fibre level. This unique property gives the carpet a special characteristic and plays a key role in its design.

## Installation Instructions

In order to ensure a precise seam cut within the nap alley, the nap alley must first be opened with a pile reamer before making an accurate cut with a seam cutter (e.g. from Mittag).

Data status 30.06.2025. Subject to changes due to technical advancements.



H