



Name of article	Highloop	Secondary backing ISO 2424	Action back
Method of production ISO 2424	Getuftet	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Schlinge	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Uni	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100% PA 6.6	Water fastness EN ISO 105 E01	4
Primary backing ISO 2424	PP	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 2120 g/m ²	Stitch rate ISO 1763	ca. 92000/m ²
Overall thickness ISO 1765	ca. 7,6 mm		
Pile service weight	ca. 1150 g/m ²		




EN 14041 | DOP: 1060-OC-3547
CPR: 1658-CPR-3547 | NB: 1658

Health-promoting properties AIR



- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers

HEALTH



Health-promoting ACOUSTIC properties



- Improved impact sound insulation +24dB
- Enhanced room acoustics +0.2α_w
- | Hz | 125 | 250 | 500 | 1000 | 2000 | 4000 |
|----------------|------|------|------|------|------|------|
| α _s | 0,01 | 0,04 | 0,11 | 0,37 | 0,36 | 0,42 |
- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective



Environmental properties

OFDDE187
PRODID | product pass

- Recycled primary backing
- Easy cleaning with water only



Product Information

The loop quality has a lively, wool-like surface structure. The delayed regeneration behavior of the tufting is typical of the fabric. Indentations in the fibers recover after a short period of frequent use.

Installation Instructions

The precise seam cut is carried out professionally using a steel ruler and a laying knife with a trapezoidal blade. The use of pile scissors is recommended for processing cut studs to ensure a flawless appearance.



Made in Europe (production according to EU standard)