

Characteristic features EN 1307



Name of article	Loft	Secondary backing ISO 2424	Conductive action back
Method of production ISO 2424	Getuftet	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Shag	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Uni	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100 % Polyamid	Water fastness EN ISO 105 E01	4
Primary backing ISO 2424	PP	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 2100 g/m ²	Stitch rate ISO 1763	ca. 23500/m ²
Overall thickness ISO 1765	ca. 7.5 mm		
Pile service weight	ca. 900 g/m ²		



EN 14041 | DOP: 1060 OC 3379 | NB: 1658

Health-promoting properties AIR

- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers



Health-promoting ACOUSTIC properties

- Improved impact sound insulation +24dB
- Enhanced room acoustics +0.3α_w

Hz	125	250	500	1000	2000	4000
α _s	0,03	0,09	0,19	0,55	0,35	0,35

- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective



Environmental properties

28ECFFBF
PRODIS-ID | product pass

- Recycled primary backing
- Easy cleaning with water only



Product Information

The high-pile yarn structure creates a soft surface look and a particularly homogeneous appearance.

Installation Instructions

An accurate, professional seam cut is made on the back of this shag quality, inside the nap, using a chopping knife. The use of "pile clamps" should be avoided; alternatively, it is recommended that the pile is carefully taped to the side with masking tape, which can be easily removed after insertion.



Made in Europe (production according to EU standard)