

Characteristic features EN 1307



Name of article	Madra 1100	Secondary backing ISO 2424	Conductive action back
Method of production ISO 2424	Tufted	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Cut	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Uni	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100% PA 6.6	Water fastness EN ISO 105 E01	≥ 4
Primary backing ISO 2424	PES	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 2500 g/m ²	Stitch rate ISO 1763	ca. 178.000/m ²
Overall thickness ISO 1765	ca. 8,0 mm		
Pile service weight	ca. 1100 g/m ²		



EN 14041 | DOP: 1060 OC 3379 | NB: 1658

Health-promoting properties AIR

- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers



Health-promoting ACOUSTIC properties

- Improved impact sound insulation +28dB
- Enhanced room acoustics +0.25α_w

Hz	125	250	500	1000	2000	4000
α _s	0,00	0,05	0,15	0,35	0,55	0,65

- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective



Environmental properties

AOF36142
PRODIS-ID | product pass

- Recycled primary backing
- Easy cleaning with water only



Product Information

The crimped velour with a high material density is characterized by deliberately incorporated iridescent shadows that reveal a varying fibre level. This unique property gives the carpet a special characteristic and plays a key role in the design.

Installation Instructions

In order to ensure a precise seam cut within the nap alley, the nap alley must first be opened with a pile reamer before making an accurate cut with a seam cutter (e.g. from Mittag).



Made in Europe (production according to EU standard)