Characteristic features EN 1307



Name of article

Method of production ISO 2424

Width ISO 3018

Surface structure ISO 2424

Colourways

Pile material ISO 2424

Primary backing ISO 2424

Overall weight ISO 8543

Overall thickness ISO 1765

Pile service weight

Maxime

Getuftet

ca. 400

Velours

Uni

100 % Polyamid

ca. 2850 g/m^2

ca. 11 mm

ca. 1850 g/m^2

Secondary backing ISO 2424

Electrostatic loading ISO 6356

Surface resistivity ISO 10965 ROT

Transparency to heat ISO 8302

Light fastness ISO 105-B02

Water fastness EN ISO 105 E01 Friction fastness EN ISO 105-X12

Stitch rate ISO 1763

Conductive action back

< 2 KV

 $10^9 \Omega$

0,09 K*m²/W

> 5

4

> 3-4

ca. $52500/m^2$



















EN 14041 | DOP: 1060 OC 3379 | NB: 1658











Health-promoting properties AIR





- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers



Health-promoting ACOUSTIC properties



• Improved impact sound insulation +30dB Enhanced room acoustics $+0.35\alpha_{w}$

					2000	
α_{S}	0,01	0,04	0,15	0,38	0,65	0,75

- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective







Environmental properties

- Recycled primary backing
- · Easy cleaning with water only















BREEAM

Made in Europe (production according to EU standard)

Product Information

The voluminous top design creates a soft surface look and a particularly homogeneous appearance.

Installation Instructions

An accurate, professional seam cut is made on the back of this shag quality, inside the nap, using a chopping knife. The use of "pile clamps" should be avoided; alternatively, it is recommended that the pile is carefully taped to the side with masking tape, which can be easily removed after insertion.

