

## Characteristic features EN 1307



Name of article	<b>AT Maxime</b>	Secondary backing ISO 2424	Welltex® Acoustic
Method of production ISO 2424	Getuftet	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 50x50	Surface resistivity ISO 10965 ROT	10 <sup>9</sup> Ω
Surface structure ISO 2424	Velours	Transparency to heat ISO 8302	0,09 K*m <sup>2</sup> /W
Colourways	Uni	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100 % Polyamid	Water fastness EN ISO 105 E01	4
Primary backing ISO 2424	PES	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 3800 g/m <sup>2</sup>	Stitch rate ISO 1763	ca. 52500/m <sup>2</sup>
Overall thickness ISO 1765	ca. 11 mm		
Pile service weight	ca. 1850 g/m <sup>2</sup>		



EN 14041 | DOP: 1060 OC 3379 | NB: 1658

### Health-promoting properties AIR

- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers



### Health-promoting ACOUSTIC properties

- High acoustic effectiveness as standard
  - Improved impact sound insulation +28dB
  - Enhanced room acoustics +0.25α<sub>w</sub>
- |                |     |     |     |      |      |      |
|----------------|-----|-----|-----|------|------|------|
| Hz             | 125 | 250 | 500 | 1000 | 2000 | 4000 |
| α <sub>s</sub> | 0,  | 0,  | 0,  | 0,   | 0,   | 0,   |
- Increased employee concentration and motivation through enhanced well-being



### Environmental properties

14FEC823  
PRODIS-ID | product pass

- Completely recyclable
- Recycled primary backing
- 100% recycled secondary backing
- Weight reduction of up to 50%
- Easy cleaning with water only



### Product Information

### Installation Instructions



Made in Europe (production according to EU standard)

Data status 21.04.2024. Subject to changes due to technical advancements.