Characteristic features EN 1307



Name of article Moody 2000 Method of production ISO 2424 Tufted Width ISO 3018 ca. 400 Surface structure ISO 2424 Cut Colourways Uni Pile material ISO 2424 100% PA 6.6 Primary backing ISO 2424 **PES** Overall weight ISO 8543 ca. 2865 g/m^2 Overall thickness ISO 1765 ca. 14.0 mm ca. 2040 g/m^2 Pile service weight

Secondary backing ISO 2424 Action back Electrostatic loading ISO 6356 < 2 KV Surface resistivity ISO 10965 ROT Transparency to heat ISO 8302 0,09 K*m² /W Light fastness ISO 105-B02 ≥ 5 Water fastness EN ISO 105 E01 ≥ 4 Friction fastness EN ISO 105-X12 $\geq 3-4$ Stitch rate ISO 1763 ca. 292.500/m²


















EN 14041 | DOP: 1060-OC-01br-2 CPR: CE System 3 | NB: 1658










- Free from PVC and bitumen.
- · Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers



Health-promoting ACOUSTIC properties



- Improved impact sound insulation +28dB
 Enhanced room acoustics +0.3α_w
- Hz 125 250 500 1000 2000 4000 α_s 0, 0, 0, 0, 0,
- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective



Environmental properties

PRODIS-ID | product pass



Easy cleaning with water only



Product Information

The velour with a voluminous, calm surface structure is characterized by deliberately incorporated iridescent shadows that reveal a varying fibre level. This unique property gives the carpet a special characteristic and plays a key role in the design.

Installation Instructions

In order to ensure a precise seam cut within the nap alley, the nap alley must first be opened with a pile reamer before making an accurate cut with a seam cutter (e.g. from Mittag).















Made in Europe (production according to EU standard)

Data status 30.06.2025. Subject to changes due to technical advancements.

