## Characteristic features EN 1307

Name of article Method of production ISO 2424 Width ISO 3018 Surface structure ISO 2424 Colourways Pile material ISO 2424 Primary backing ISO 2424 Overall weight ISO 8543 Overall thickness ISO 1765 Pile service weight	<b>Nylloop 600</b> Tufted ca. 400 Loop Mix 100% Econyl by Aquafil PES ca. 1900 g/m <sup>2</sup> ca. 5,5 mm ca. 600 g/m <sup>2</sup>	Secondary backing ISO 2424 Electrostatic loading ISO 6356 Surface resistivity ISO 10965 ROT Transparency to heat ISO 8302 Light fastness ISO 105-B02 Water fastness EN ISO 105 E01 Friction fastness EN ISO 105-X12 Stitch rate ISO 1763	Action back < 2 KV 10 <sup>9</sup> Ω 0,09 K*m² /W ≥ 6 ≥ 5 ≥ 5 ca. 150.100/m²
		<b>CE</b> EN 14041   DOP: 1060-OC-3379 CPR: 1658-CPR-3379   NB: 1658	
<ul> <li>Health-promoting properties AIR O</li> <li>Free from PVC and bitumen.</li> <li>Free from formaldehyde.</li> </ul>		<ul> <li>Health-promoting ACOUSTIC properties →</li> <li>Improved impact sound insulation +25dB Enhanced room acoustics +0.2a<sub>w</sub></li> </ul>	

HEALTH

- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.

**Environmental properties** 

- TVOC limits are immediately met.
- Suitable for allergy sufferers

266E7C80 PRODIS-ID | product pass

70 710 3720-1

- 100% recycled yarn
- Recycled primary backing
- Easy cleaning with water only



## **Product Information**

The fabric surface of bouclé velour is characterized by a lively surface appearance. The delayed regeneration behavior of the fibers is typical of the loop quality. Impression marks recover after a short period of use.

250

0,05

through enhanced well-being

125

0,01

Acoustically effective

Hz

 $\alpha_{s}$ 

500

0,10

Increased employee concentration and motivation

1000

0,25

2000

0,44

4000

0,45

## Installation Instructions

An accurate, professional seam cut is made on the back of this shag quality, inside the nap, using a chopping knife. The use of "pile clamps" should be avoided; alternatively, it is recommended that the pile is carefully taped to the side with masking tape, which can be easily removed after insertion.

Data status 30.06.2025. Subject to changes due to technical advancements.



 $(\mathbf{0})$