

Characteristic features EN 1307

Name of article	AT Nyllloop 600	Secondary backing ISO 2424	Welltex® Acoustic
Method of production ISO 2424	Tufted	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 50x50	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Loop	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Mix	Light fastness ISO 105-B02	≥ 6
Pile material ISO 2424	100% Econyl by Aquafil	Water fastness EN ISO 105 E01	≥ 5
Primary backing ISO 2424	PES	Friction fastness EN ISO 105-X12	≥ 5
Overall weight ISO 8543	ca. 2000 g/m ²	Stitch rate ISO 1763	ca. 150.100/m ²
Overall thickness ISO 1765	ca. 5,5 mm		
Pile service weight	ca. 600 g/m ²		



EN 14041 | DOP: 1060-OC-3497
CPR: 1658-CPR-3497 | NB: 1658

Health-promoting properties AIR

- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers

HEALTH

70 710 3720-8



Health-promoting ACOUSTIC properties

- High acoustic effectiveness as standard
- Improved impact sound insulation +28dB
- Enhanced room acoustics +0.25α_w

Hz	125	250	500	1000	2000	4000
α _s	0,00	0,05	0,30	0,25	0,25	0,35

- Increased employee concentration and motivation through enhanced well-being



Environmental properties

EB99B4EC
PRODUSID | product pass

- Completely recyclable
- 100% recycled yarn
- Recycled primary backing
- 100% recycled secondary backing
- Weight reduction of up to 50%
- Easy cleaning with water only



Product Information

AT NYLLOOP - This tile stands out with its mélange loop that creates a tiled appearance. Especially in lighter colors, the tile pattern becomes distinctly visible due to the shadow effects in the tile joints. During initial use, this appearance develops significantly thanks to daily maintenance with a brush vacuum cleaner. Experience how the tiles gain individual beauty over time.

Installation Instructions



Made in Europe (production according to EU standard)

Data status 30.06.2025. Subject to changes due to technical advancements.