

Characteristic features EN 1307



Name of article	Nylrips 900	Secondary backing ISO 2424	Conductive action back
Method of production ISO 2424	Tufted	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Loop	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Uni	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100% PA 6.6 Gespinst	Water fastness EN ISO 105 E01	≥ 4
Primary backing ISO 2424	PA, PP	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 2300 g/m ²	Stitch rate ISO 1763	ca. 92.500/m ²
Overall thickness ISO 1765	ca. 6,0 mm		
Pile service weight	ca. 800 g/m ²		



EN 14041 | DOP: 1060 OC 3379 | NB: 1658

Health-promoting properties AIR

- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers



Health-promoting ACOUSTIC properties

- Improved impact sound insulation +25dB
Enhanced room acoustics +0.2α_w

Hz	125	250	500	1000	2000	4000
α _s	0,01	0,05	0,10	0,25	0,44	0,45

- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective



Environmental properties

EADD1EAA
PRODISID | product pass

- Recycled primary backing
- Easy cleaning with water only



Product Information

Different loop constructions create a graphic, woolly texture. The delayed regeneration behavior of the tufting is typical of the fabric. Indentations in the fibers recover after a short period of frequent use.

Installation Instructions

The seam is cut professionally from above within the nap alley using a seam cutter (e.g. from Mittag). During this work process, it must be ensured that the nap alley is not left during cutting.



Made in Europe (production according to EU standard)

Data status 21.04.2024. Subject to changes due to technical advancements.