Characteristic features EN 1307



Name of article

Method of production ISO 2424

Width ISO 3018

Surface structure ISO 2424

Colourways

Pile material ISO 2424

Primary backing ISO 2424

Overall weight ISO 8543

Overall thickness ISO 1765

Pile service weight

Nylrips 900

Tufted

ca. 400

Loop

Uni

100% PA 6.6 Gespinst

PA, PP

ca. 2300 g/m²

ca. 6,0 mm

ca. 800 g/m^2

Secondary backing ISO 2424

Electrostatic loading ISO 6356

Surface resistivity ISO 10965 ROT

Transparency to heat ISO 8302

Light fastness ISO 105-B02 Water fastness EN ISO 105 E01

Friction fastness EN ISO 105-X12

Stitch rate ISO 1763

Action back < 2 KV

 $10^9 \Omega$

 $0.09 \, K^* m^2 / W$

> 5

> 4

> 3-4

ca. $92.500/m^2$

















EN 14041 | DOP: 1060-OC-3379 CPR: 1658-CPR-3379 | NB: 1658

















- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers










HEALTH

Health-promoting ACOUSTIC properties



Hz	125	250	500	1000	2000	4000
α_{S}	0,01	0,05	0,10	0,25	0,44	0,45

- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective

Environmental properties

EADD1EAA

· Easy cleaning with water only

· Recycled primary backing













Made in Europe (production according to EU standard)

Product Information

Different loop constructions create a graphic, woolly texture. The delayed regeneration behavior of the tufting is typical of the fabric. Indentations in the fibers recover after a short period of frequent use.

Installation Instructions

The seam is cut professionally from above within the nap alley using a seam cutter (e.g. from Mittag). During this work process, it must be ensured that the nap alley is not left during cutting.

