



Name of article	Nyltecc 700	Secondary backing ISO 2424	Action back
Method of production ISO 2424	Tufted	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Cut	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Mix	Light fastness ISO 105-B02	≥ 6
Pile material ISO 2424	100% Econyl by Aquafil	Water fastness EN ISO 105 E01	≥ 5
Primary backing ISO 2424	PA, PP	Friction fastness EN ISO 105-X12	≥ 5
Overall weight ISO 8543	ca. 2000 g/m ²	Stitch rate ISO 1763	ca. 165.900/m ²
Overall thickness ISO 1765	ca. 6,0 mm		
Pile service weight	ca. 730 g/m ²		



EN 14041 | DOP: 1060-OC-3379
CPR: 1658-CPR-3379 | NB: 1658

Health-promoting properties AIR



- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers

HEALTH



70 710 3720-1



Health-promoting ACOUSTIC properties



- Improved impact sound insulation +25dB
- Enhanced room acoustics +0.2α_w
- | Hz | 125 | 250 | 500 | 1000 | 2000 | 4000 |
|----------------|------|------|------|------|------|------|
| α _s | 0,01 | 0,05 | 0,10 | 0,25 | 0,44 | 0,45 |
- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective



Environmental properties

31548F8F
PRODISID | product pass

- 100% recycled yarn
- Recycled primary backing
- Easy cleaning with water only



Product Information

The cut pile carpet made from dyed-through solution dyed fibres is characterized by particularly high colour and light fastness and durability.

Installation Instructions

In order to ensure a precise seam cut within the nap alley, the nap alley must first be opened with a pile reamer before making an accurate cut with a seam cutter (e.g. from Mittag).



Made in Europe (production according to EU standard)

Data status 30.06.2025. Subject to changes due to technical advancements.