



Name of article	Savoy 1100	Secondary backing ISO 2424	Action back
Method of production ISO 2424	Tufted	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Loop	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Style	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100% Econyl by Aquafil	Water fastness EN ISO 105 E01	≥ 4
Primary backing ISO 2424	PA, PES	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 2250 g/m ²	Stitch rate ISO 1763	ca. 182.700/m ²
Overall thickness ISO 1765	ca. 8,0 mm		
Pile service weight	ca. 1150 g/m ²		



EN 14041 | DOP: 1045-120905 | NB: 1658

Health-promoting properties AIR



- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers

HEALTH



Health-promoting ACOUSTIC properties



- Improved impact sound insulation +28dB
- Enhanced room acoustics +0.2α_w

Hz	125	250	500	1000	2000	4000
α _s	0,00	0,05	0,10	0,25	0,45	0,50

- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective



Environmental properties

8E3C4EF4
PRODID:ID | product pass

- 100% recycled yarn
- Recycled primary backing
- Easy cleaning with water only



Product Information

Different loop constructions create a graphic, woolly texture. The delayed regeneration behavior of the tufting is typical of the fabric. Indentations in the fibers recover after a short period of frequent use

Installation Instructions

The expressive loop quality creates a lively, melange-like surface appearance. The delayed regeneration behavior of the tufting quality is typical of the product. Indentations in the fibers recover after a short period of use.



Made in Europe (production according to EU standard)

Data status 23.07.2024. Subject to changes due to technical advancements.