

Characteristic features EN 1307



Name of article	Twist 600	Secondary backing ISO 2424	Conductive action back
Method of production ISO 2424	Tufted	Electrostatic loading ISO 6356	< 2 KV
Width ISO 3018	ca. 400	Surface resistivity ISO 10965 ROT	10 ⁹ Ω
Surface structure ISO 2424	Loop	Transparency to heat ISO 8302	0,09 K*m ² /W
Colourways	Mix	Light fastness ISO 105-B02	≥ 5
Pile material ISO 2424	100% Econyl by Aquafil	Water fastness EN ISO 105 E01	≥ 4
Primary backing ISO 2424	PES	Friction fastness EN ISO 105-X12	≥ 3-4
Overall weight ISO 8543	ca. 1750 g/m ²	Stitch rate ISO 1763	ca. 154.800/m ²
Overall thickness ISO 1765	ca. 5,8 mm		
Pile service weight	ca. 600 g/m ²		



EN 14041 | DOP: 1060 OC 3379 | NB: 1658

Health-promoting properties AIR

- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers



Health-promoting ACOUSTIC properties

- Improved impact sound insulation +23dB
- Enhanced room acoustics +0.2α_w

Hz	125	250	500	1000	2000	4000
α _s	0,00	0,05	0,10	0,30	0,50	0,60

- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective



Environmental properties

ED22963E
PRODISID | product pass

- Recycled primary backing
- Easy cleaning with water only



Product Information

Yarn loops in different shades and degrees of gloss create a lively, harmonious texture. The delayed regeneration behavior of the tufting is typical of the product. Indentations in the fibers recover after a short period of frequent use.

Installation Instructions

The precise seam cut is carried out professionally using a steel ruler and a laying knife with a trapezoidal blade. The use of pile scissors is recommended for processing cut studs to ensure a flawless appearance.



Made in Europe (production according to EU standard)