Characteristic features EN 1307



Name of article

Method of production ISO 2424

Width ISO 3018

Surface structure ISO 2424

Colourways

Pile material ISO 2424

Primary backing ISO 2424

Overall weight ISO 8543 Overall thickness ISO 1765

Pile service weight

Twist 600

Tufted

ca. 400

Loop

Mix

100% Econyl by Aquafil

PES

ca. 1750 g/m^2

ca. 5,8 mm

ca. 600 g/m^2

Secondary backing ISO 2424

Electrostatic loading ISO 6356

Surface resistivity ISO 10965 ROT

Transparency to heat ISO 8302 Light fastness ISO 105-B02

Water fastness EN ISO 105 E01

Friction fastness EN ISO 105-X12

Stitch rate ISO 1763

Action back

< 2 KV

 $10^9 \Omega$

 $0.09 \, K^* m^2 / W$

> 5

> 4 > 3-4

ca. $154.800/m^2$



















EN 14041 | DOP: 1060-OC-3547 CPR: 1658-CPR-3547 | NB: 1658















- Free from PVC and bitumen.
- Free from formaldehyde.
- Reduction of fine dust in the breathing air.
- Free from harmful emissions and odors.
- TVOC limits are immediately met.
- Suitable for allergy sufferers



70 710 3720-1







Health-promoting ACOUSTIC properties



- Improved impact sound insulation +23dB Enhanced room acoustics $+0.2\alpha_{\omega}$
 - 250 500 1000 2000 125 4000 0,10 0,00 0,05 0,30 0,50 0,60
- Increased employee concentration and motivation through enhanced well-being
- Acoustically effective

Environmental properties

ED22963E PRODIS-ID | product pass

- Recycled primary backing
- · Easy cleaning with water only

BREEAM















Product Information

Yarn loops in different shades and degrees of gloss create a lively, harmonious texture. The delayed regeneration behavior of the tufting is typical of the product. Indentations in the fibers recover after a short period of frequent use.

Installation Instructions

The precise seam cut is carried out professionally using a steel ruler and a laying knife with a trapezoidal blade. The use of pile scissors is recommended for processing cut studs to ensure a flawless appearance.

